

TECHNICAL PROPERTIES OF ZL® 900H NAT (ACETAL HOMOPOLYMER, NATURAL)

Property		Units	Test Method ASTM	Value
MECHANICAL PROPERTIES				
Specific Gravity		gm/cm ³	D-792	1.42
Tensile Strength	73 °F	psi	D-638	10,000
Tensile Modulus	73 °F	psi	D-638	450,000
Elongation, Break	73 °F	%	D-638	40
Flexural Strength	73 °F	psi	D-790	14,100
Flexural Modulus	73 °F	psi	D-790	450,000
Compressive Strength	73 °F	psi	D-695	16,000
Compressive Modulus		psi	D-695	450,000
Impact Strength, Notched	73 °F	ft-lbs/in	D-256	1.5
Hardness, Rockwell		R	D-785	R122 (M94)
Hardness, Durometer, Shore D		D	2240	D86
Shear Strength		psi	D-732	9,000
Coefficient of Friction, against steel		-	-	0.15
THERMAL PROPERTIES				
Deflection Temperature	66 psi	°F	D-648	340
	264 psi	°F	D-648	277
Maximum Temperature - Long Term		°F	-	180
Maximum Temperature - Short Term		°F	-	-
Melting Point		°F		347
Coefficient of Linear Thermal Expansion		in/in/°F	D-696	4.7 x 10 ⁻⁵
Thermal Conductivity		Btu-in/hr-ft ² -°F	C-177	2.5
ELECTRICAL PROPERTIES				
Dielectric Strength		V/mil	D-149	3,000
Dielectric Constant	1 kHz	-	D-150	3.7
Dissipation Factor	1 kHz		D-150	0.005
Flammability			UL 94	HB
Volume Resistivity	73 °F	Ω.cm	D-257	10 ¹⁵
WATER ABSORPTION RATES				
Water Absorption at 73 °F	24 hours	%	D-570	0.25
	Saturation	%	D-570	0.9

All statements, technical information and recommendations contained in this brochure are presented in good faith, but all information is given without warranty and liability. The reader is cautioned, however that ZL Engineering Plastics cannot guarantee the accuracy or completeness of this information, and it is the customer's responsibility to determine the suitability of ZL™ products in any given application.