

TECHNICAL PROPERTIES OF ZL™ 250 MO (Extruded Nylon 6/6, MoS₂-filled)

Property		Units	Test Method ASTM	Value
MECHANICAL PROPERTIES				
Specific Gravity		gm/cm ³	D-792	1.16
Tensile Strength	73 °F	psi	D-638	10,000 - 14,000
Tensile Modulus	73 °F	psi	D-638	480,000
Elongation, Break	73 °F	%	D-638	120
Flexural Strength	73 °F	psi	D-790	17,000
Flexural Modulus	73 °F	psi	D-790	460,000
Compressive Strength	73 °F	psi	D-695	16,000
Compressive Modulus		psi	D-695	420,000
Impact Strength, Notched	73 °F	ft-lbs/in	D-256	0.5
Hardness, Rockwell		R	D-785	R125
Hardness, Durometer, Shore D		D	2240	D85
Shear Strength		psi	D-732	10,500
Coefficient of Friction, against steel		-	-	0.20
THERMAL PROPERTIES				
Deflection Temperature	66 psi	°F	D-648	-
	264 psi	°F	D-648	200
Maximum Temperature - Long Term		°F	-	220
Maximum Temperature - Short Term		°F	-	-
Melting Point		°F		500
Coefficient of Linear Thermal Expansion		in/in/°F	D-696	4 x 10 ⁻⁵
Thermal Conductivity		Btu-in/hr-ft ² -°F	C-177	1.7
ELECTRICAL PROPERTIES				
Dielectric Strength		V/mil	D-149	350
Dielectric Constant	1 kHz	-	D-150	3.7
Dissipation Factor	1 kHz		D-150	0.02
Flammability			UL 94	V-2
Volume Resistivity	73 °F	Ω.cm	D-257	-
WATER ABSORPTION RATES				
Water Absorption at 73 °F	24 hours	%	D-570	1.0
	Saturation	%	D-570	7.0

All statements, technical information and recommendations contained in this brochure are presented in good faith, but all information is given without warranty and liability. The reader is cautioned, however that ZL Engineering Plastics cannot guarantee the accuracy or completeness of this information, and it is the customer's responsibility to determine the suitability of ZL™ products in any given application.